

TEST REPORT

Mechanical & Hardgoods Lab

Report No. : HLD0064/2012

Page : 1 of 2

Date : DEC. 14, 2012

SUPER SHENG ENTERPRISES CO., LTD

No. 6, Lane 151, Minsheng St., Sanhsia Dist., New Taipei City, Taiwan 23741

The following merchandise was submitted and identified by the applicant as:

Product Description: Gas Spring-Piston Rod (Nitrided Black)
Style/Item No.: C150385-L3-XXXNA
Manufacturer/Vendor: SUPER SHENG ENTERPRISES CO., LTD
Country of Origin: TAIWAN

We have tested the submitted sample(s) as requested and the following results were obtained:

Test Requested: Neutral Salt Spray Test (Refer to ISO 9227:2012)

Test Method:

Placed the sample in the testing machine and set the condition as below, then take it out and examine.

Note: The test condition of salt spray test


1. Salt solution concentration : 5%
2. pH value : 6.5 – 7.2
3. Air supply : between 70 kPa to 170 kPa
4. Temperature in salt spray chamber : 35°C
5. Time : 24 hours

Test Result: --- See attached sheets ---

Date of Receipt: Dec. 05, 2012

Testing Period: Dec. 05, 2012 ~ Dec. 13, 2012

Signed for and on behalf of
SGS Taiwan Ltd.



Jackson Chen
Team Leader

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/en/Terms-and-Conditions/Terms-e-Document. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.


Test Result:

ASSESSMENT OF PROTECTION RATING AND APPEARANCE RATING:

Rating	Area of defects (ISO 10289) A (%)
10	No defects
9	$0 < A \leq 0.1$
8	$0.1 < A \leq 0.25$
7	$0.25 < A \leq 0.5$
6	$0.5 < A \leq 1.0$
5	$1.0 < A \leq 2.5$
4	$2.5 < A \leq 5.0$
3	$5.0 < A \leq 10$
2	$10 < A \leq 25$
1	$25 < A \leq 50$
0	$50 < A$

SAMPLE	TIME	OBSERVATION	RATING
Gas Spring-Piston Rod (Nitrided Black)	24 hours	$0.1 < A \leq 0.25$	8

- Picture(s) -



--- End of Report ---

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.