

TEST REPORT

Report No.: HL40444/2013

1

Page No.:

of

Date:

MAY 02, 2013

SUPER SHENG ENTERPRISE CO., LTD.

No. 6, Lane 151, Minsheng St., Sanhsia Dist., New Taipei City, Taiwan 23741

The following merchandise was submitted and identified by the applicant as:

Product Description:

SUPERSEN BRACKET

Style/Item No.:

BKT-09C

Country of Origin:

TAIWAN

We have tested the submitted sample(s) as requested and the following results were obtained:

Test Requested:

Tensile strength test

Test Methods:

- 1. Hook a steel cable on the outer edge of protruding shaft that is parallel with
 - Platform
- 2. Apply an upward load by means of testing machine, until it is damaged then
 - record the max. force.
- 3. Testing Machine: INSTRON 5581; Speed: 10 mm/min.
- 4. Diameter of steel cable: Ø 3.0 mm

Test Results:

Sample	Max. force (kgf)	Failure mode
BKT-09C	219.58	The sample was broken after testing. (Photo B)

Quantity of tested sample: 1 pcs

Date of Receipt:

Apr. 23, 2013

Testing Period:

Apr. 23, 2013 ~ May 02, 2013

Signed for and on behalf of SGS Taiwan Ltd.

Jackson Chen

Team Leader



TEST REPORT

Report No.: HL40444/2013

Page No.: 2 of

- Picture(s) -



Photo A: Appearance of the sample



Photo B: After testing

-- End of Report--